

**FILM WASHI**  
world's smallest film company

**I**  
80 ISO  
DATA SHEET

## INDUSTRIAL X-RAY FILM

**Sensitivity :** 80 ISO  
**Grain :** fine  
**Contrast :** strong

**Production process :** industrial coating  
**Base :** Blue polyester, 175 µm

**Spectral sensitivity :** Maximum 550 nm  
**Darkroom safelight :** Red, 575 nm



**Original use :** "I" , is originally used for industrial examination through X-rays. Being coated on both side and without anti-halation layer, it create a very special aesthetic.


**Recommended use :** Landscape, urban photography, still life. Portrait,

### Processing :

exposure	developer	dilution	time	T°C
80 iso	Ultrafin	1+10	4 mn	20°C
80 iso	D-76	1+1	4,5 mn	20°C
80 iso	Rodinal	1+25	6 mn	20°C
80 iso	Ilfosol 3	1+9	6,5 mn	20°C
80 iso	Ilfotec LC29	1+19	6,5 mn	20°C

For using with an unlisted developer, you can use, for a 80 iso exposure, times and dilution of Ilford HP5 at 400 iso.

### Structure of layers :



**Loading :** 120 roll films can be loaded like any normal film but being thicker than usual it needs to be kept wounded tight while loading and unloading

**Standard sizes :** 120 roll

**Usage tips :** Radiographic film are more fragile than others and need extra care during all part of use and process to avoid any risk of scratch.

.....  
*We take great care in the manufacture of each Film. If you are unhappy with the film for any reason please get in touch and we will do our best to help. In case of manufacturing defect, films will be replaced by new ones. No other claims for compensation will be accepted.*

FILM WASHI EURL ☒ 22, rue Albert Camus|44600 Saint-Nazaire|France

☎ 00.(33)6.79.29.71.53 ✉ contact@filmwashi.com

No TVA Intracommunautaire : FR 71817963028

